

CAPPING GYPSUM COMPOUND

Standard: ASTM C617/AASHTO T231

Capping Compound

Gypsum capping compound for high strength capping preparation, it can achieve strength from 5000 - 9000 psi (350~630 kgf/cm²) after mixing with water for 30 mins. Gypsum is a fast, safer, easier and cheaper method compound with sulfure capping, rubber pad capping and grinding process.

Technical Specifications :

Model Number	NL 4009 X / 006A	NL 4009 X / 006B
Packing Code	S-350	S-630
Compressive Strength	350 kgf/cm ² (34 MPa)	630 kgf/cm ² (62 MPa)
Water Mix Ratio	23 ~ 24 %	15.5 ~ 16 %
Curing Time	30 min	30 min
Pack Weight	25 kg/pack	25 kg/pack

Optional Accessories :

Model Number	Parts Description	Qty
NL 4009 X / 006 - P 001	Glass Plater 200 X 200 X 8 mm	1no.
NL 4009 X / 006 - P 002	Mixing Bowl come with Spatula	1no.
NL 4009 X / 006 - P 003	Levelling Device	1no.



S-630



S-350



Optional Accessories

